

Entwicklungs- und Prueflabor Holztechnologie GmbH · Zellescher Weg 24 · 01217 Dresden · Germany

HEMEL EMPRENYE SANAYI VE TICARET A.S.
Mr. Mert Çakır
I.D.O.S.B VAKUM CAD. NO:25 B1 OZEL PARSEL
TUZLA,34957, ISTANBUL
TÜRKEI

Entwicklungs- und Prueflabor
Holztechnologie GmbH
Zellescher Weg 24
01217 Dresden · Germany

Phone: +49 351 4662 0
Fax: +49 351 4662 211
info@eph-dresden.de
www.eph-dresden.de

Dresden, 16/01/2019
MPET

Test Report Order No. 2718577/1

Client: HEMEL EMPRENYE SANAYI VE TICARET A.S.
I.D.O.S.B VAKUM CAD. NO:25 B1 OZEL PARSEL
TUZLA,34957, ISTANBUL
TÜRKEI

Date of order: 03/01/2019

Order: Determination of the resistance against scratching
according to EN 15186:2012 procedure B

Contractor: EPH – Laboratory Surface Testing

Engineer in charge: Dipl.-Ing. (FH) M. Peter



Dr.-Ing. Rico Emmmler

Head of Laboratory Surface Testing

The test report contains 3 pages. Any duplication, even in part, requires written permission of EPH.
These test results are exclusively related to the tested material.

1 Task

The Development and Examination Laboratory for Wood Technology Ltd. (EPH) was instructed by HEMEL EMPRENYE SANAYI VE TICARET A.S. in ISTANBUL, TÜRKİYE to carry out the resistance against scratching according to EN 15186:2012 procedure B.

2 Material

For the test, the customer has sent three samples of a lacquered parquet (entrance at the EPH laboratory 07/01/2019)

The samples were labelled as follows:

HEMEL Ultramat 2C

3 Determination of the resistance to scratching according to DIN EN 15186:2012

The test was carried out according to DIN EN 15186:2012 procedure B with a universal Scratch Tester Model 413 (Erichsen, Germany).

The tests were carried out on: 15/01/2019 – 16/01/2019.

4 Result

Scratching load in N, which causes an in itself closed mark			
Single values			Mean value
1.2	1.4	1.2	1.3

5 Evaluation


Normative requirements for the resistance against scratching of lacquered parquets are no existing. That's why the result will be compared with the "IHD-Requirement Profile for wooden flooring - lacquered surfaces" in level of use (LU 1: private living area with moderate use....LU 6: area of object with heavy use) as following:

Property	Result	Assessment in level of use
Resistance against scratching according to DIN EN 15186:2012 procedure B	1,3 N	LU 1 – 6 fulfilled*

- * Requirement for the LU1-LU2: ≥ 0.5 N
 Requirement for the LU3-LU4: ≥ 0.7 N
 Requirement for the LU5-LU6: ≥ 1.0 N

Level of use for lacquered wooden floorings according to IHD-profile

Level of use	Area of use	Intensity / description of requirements	Examples for use
1	domestic	moderate / rare use	Bedroom, guestroom
2	domestic	general / often normal use	Living room, dining room, studying room
3	domestic	heavy / intensive use	Entry-corridor, children's room, kitchen
4	commercial	moderate / rare use	Hotel room
5	commercial	general / often normal use	boutiques or small stores
6	commercial	heavy / intensive use	department stores and multipurpose halls


 Dipl.-Ing. (FH) M. Peter
 Engineer in charge